

# isola

## 370 TURBO®

### High Performance Laminate and Prepreg Materials

370 TURBO offers a 175°C glass transition temperature (T<sub>g</sub>) and 340°C degradation temperature (T<sub>d</sub>), making it an ideal choice for the most thermally demanding multilayer Printed Wiring Board (PWB) applications.

The application of TURBO® manufacturing to the industry-leading 370 system provides this dramatic improvement in thermal performance and reliability. TURBO technology also results in faster curing, allowing lamination press cycle time reductions of 30% or more. This combination provides not only improved performance but retains FR-4 processability, with mechanical, chemical and moisture resistance and laser fluorescing and UV blocking properties that equal or exceed the performance of any other FR-4 material available.

### Product Attributes

Legacy Materials

#### ORDERING INFORMATION:

Contact your local sales representative or visit [www.isola-group.com](http://www.isola-group.com) for further information.

Isola Group  
3100 West Ray Road  
Suite 301  
Chandler, AZ 85226  
Phone: 480-893-6527  
Fax: 480-893-1409  
info@isola-group.com

Isola Asia Pacific (Hong Kong) Ltd.  
Unit 3512 - 3522, 35/F  
No. 1 Hung To Road, Kwun Tong,  
Kowloon, Hong Kong  
Phone: 852-2418-1318  
Fax: 852-2418-1533  
info.hkg@isola-group.com

Isola GmbH  
Isola Strasse 2  
D-52348 Düren,  
Germany  
Phone: 49-2421-8080  
Fax: 49-2421-808164  
info-dur@isola-group.com

Legacy Materials

## Data Sheet

T<sub>g</sub> 175°C

T<sub>d</sub> 340°C

D<sub>k</sub> 4.10

D<sub>f</sub> 0.022

IPC-4101 - / 21 / 24 / 26 / 121 / 124

UL - File Number E41625

Last Updated March 14, 2018  
Revision No: A

### Product Features

- Industry Recognition
  - UL File Number: E41625
  - Qualified to UL's MCIL Program
  - RoHS Compliant
- Performance Attributes
  - Lead-free assembly compatible
- Processing Advantages
  - FR-4 process compatible
  - UV blocking and AOI fluorescence

### Product Availability

- Standard Material Offering: Laminate
  - 2 to 125 mil (0.05 to 3.2 mm)
  - Available in full size sheet or panel form
- Copper Foil Type
  - HTE Grade 3
  - RTF (Reverse Treat Foil)
- Copper Weight
  - ½ to 2 oz (18 to 70 µm) available
  - Heavier copper available
  - Thinner copper foil available
- Standard Material Offering: Prepreg
  - Roll or panel form
  - Tooling of prepreg panels
- Glass Fabric Availability
  - E-glass
  - Square weave glass

Property	Typical Value	Units	Test Method	
		Metric (English)	IPC-TM-650 (or as noted)	
Test data generated from rigid laminate	50	%	2.3.16.2	
Glass Transition Temperature (Tg) by DSC	175	°C	2.4.25C	
Decomposition Temperature (Td) by TGA @ 5% weight loss	340	°C	2.4.24.6	
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	45 >10	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	50 250 3.5	ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE	Pre-Tg	13	ppm/°C	2.4.24C
Thermal Conductivity		0.35	W/mK	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 2 GHz B. @ 5 GHz	4.10 4.00	—	Bereskin Stripline
Df, Loss Tangent	@ 2 GHz	0.022	—	Bereskin Stripline
Dk, Permittivity	@ 5 GHz	0.024	—	Bereskin Stripline
Volume Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— 3.0 x 10 <sup>8</sup> 7.0 x 10 <sup>8</sup>	MΩ-cm	2.5.17.1
Surface Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— 3.0 x 10 <sup>6</sup> 7.0 x 10 <sup>8</sup>	MΩ	2.5.17.1
Dielectric Breakdown		>50	kV	2.5.6B
Arc Resistance		125	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		52 (1300)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		3 (175-249)	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil] B. Standard profile copper 1. After thermal stress 2. At 125°C (257°F) 3. After process solutions	1.23 (7.0) 1.58 (9.0) 1.23 (7.0) 1.58 (9.0)	N/mm (lb/inch)	2.4.8C 2.4.8.2A 2.4.8.3 2.4.8.3
Moisture Absorption		0.15	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Max Operating Temperature		130	°C	UL 796

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

[www.isola-group.com/products/all-printed-circuit-materials/370-turbo/](http://www.isola-group.com/products/all-printed-circuit-materials/370-turbo/)

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. 370 TURBO<sup>®</sup> is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2016, Isola Group, All rights reserved.



## NOTE

Visit our site <http://www.isola-group.com> for more details.